



## SPEKTRA interior putty

### USE

Ready made fine putty for smoothing interior wall and ceiling surfaces.

It is suitable for puttying of surfaces such as mineral plasters, concrete, plaster plates as well as for the puttying of interior wall surfaces, which are painted with dispersion paints.

It can be applied up to the thickness of 2 mm.

### CHARACTERISTICS

- Ready made smoothing material
- Suitable for manual application
- Easy treatment and polishing
- High vapour permeability

TECHNICAL DATA	
PRODUCT TYPE	vinylacetate copolymer dispersion, fillers and special additives
COLOUR SHADES	white
TINTING	/
DENSITY	1.5 – 1.6 kg/l
THINNING	with water if necessary
PACKAGING UNITS	3.5 kg, 8 kg and 25 kg
SHELF LIFE	The shelf life of the originally closed and suitably packed product (temperature from +5°C to +35°C, dry place) is until the date indicated on packaging. IT SHOULD NOT FREEZE !

INSTRUCTIONS FOR USE	
APPLICATION	stainless trowel
WORKING CONDITIONS	min. +5°C air, surface and putty
DRYING (T = +20°C, rel hum. 65%)	the coating is dry and suitable for polishing after 10 – 12 hours
COVERAGE	theoretically: 1.5 – 2 kg/m <sup>2</sup> in 2 layers Practical consumption depending on the coating thickness and surface roughness.
CLEANING OF TOOLS	immediately after use with water

### SURFACE PREPARATION

The surface should be free from dust, crumbly particles and other impurities. Remove old falling off coats. Fill up bigger cracks and damaged surface with adequate materials on the mineral basis. In case of repairs, impregnate with **SPEKTRA acrylic impregnation** or **SPEKTRA deep impregnation**. Prior to putty application, the surface should be dry and firm.

Apply **SPEKTRA biocide agent SANITOL** to wall surfaces, which are attacked by mould and algae. After the surfaces have dried, remove mould mechanically. Add **SPEKTRA protection against mould** to paint, which for the longer period prevents the growth of microorganisms or use **SPEKTRA wall paint for kitchens and bathrooms**.

Paint the spots of nicotine, water outflow, tar, water-proof pencils... with **SPEKTRA antinicotine paint**, which already represents the final coating

Clean »healthy« surfaces without cracks, which are painted with smooth, shiny or semi-shiny enamels or dispersion paint and sand them with the sanding paper (No. 150).



## COATING SYSTEMS

SURFACE	SURFACE PREPARATION	IMPREGNATION	PUTTYING	TOP COAT
<b>New not painted surface</b> - lime-cement plasters - plaster-cardboard plates  - concrete and other not porous substrates		1x <b>SPEKTRA acrylic impregnation</b>  1x <b>SPEKTRA deep impregnation</b>		<b>SPEKTRA interior wall paint</b> – at option
<b>Painted with dispersion paints</b> - several layers of permeable, not washable coatings  - smooth, shiny, washable coatings	cleaning, removal of crumbly particles, repair of damaged spots  cleaning, polishing	1x <b>SPEKTRA acrylic impregnation</b>	2x <b>SPEKTRA interior putty</b> (if necessary)	

## REMARKS

- We recommend the puttying of walls with **SPEKTRA interior putty** particularly prior to the application of decorative coatings (**SPEKTRA Domflok**) and high washable dispersion paints (**SPEKTRA latex (semi-matt)**...).
- Drying time increases at low temperatures and higher air humidity and it also depends on the layer thickness of **SPEKTRA interior putty**.