



TESSAROL professional enamel satin

USE

For the protection against the weather conditions and decortation of wood and metal surfaces such as windows, doors, fittings, wood claddings, fences, constructions, simple furniture in the interior and exterior.

CHARACTERISTICS

- semi-glossy final coating appearance
- excellent hiding power
- easy work – very simple application
- excellent sagging
- quick drying
- stable colour shade (it does almost not get yellow)
- good elasticity and hardness
- excellent weather and light resistance
- resistance to cleaners, which are used in household

| TECHNICAL DATA | |
|----------------------------|--|
| COMPOSITION | modified alkyd binder, solvent, pigment |
| COLOUR SHADES | white |
| GLOSS | sSemi-glossy |
| DENSITY | 1,2 g / ml |
| THINNING | ready for application |
| EU VOC category and limits | IIA(d), 400 g/l (2007); product contains: max. 390 g/l |
| PACKAGING UNITS | standard colour shades:0,75 l,2,5 l |
| SHELF LIFE | The shelf life of the originally closed and suitably stored product (temperature from +5°C to +35°C, dry room) is at least until the date as indicated on packaging. |

| INSTRUCTIONS FOR USE | | | | |
|------------------------------------|--|----------------------|----------------|---------------|
| APPLICATION | thinning | viscosity (DIN 4 mm) | nozzle | Pressure |
| Brush,roller | / | | | |
| spraying | | | | |
| Airless | / | delivery | 0,23 – 0,28 mm | 120 – 160 bar |
| WORKING CONDITIONS | Temperature of paint, air and facility should be minimally +5°C | | | |
| DRYING (T = +20°C, rel. hum. 65 %) | Powder dry approx. 2 hours, dry to touch 4 – 6 hours, next coat after 16 hours At a lower temperature and higher relative humidity the drying time will be prolonged. | | | |
| COVERAGE | theoretically : in one coat 10 – 12 m ² of surface with 1 l Practical consumption depends on the treatment and type of surface,application method and the selected colour shade. | | | |
| CLEANING OF TOOLS | TESSAROL thinner | | | |

PREPARATION OF SURFACE

Wood surface

The content of humidity in conifers should not exceed 15 %, in foliage plants 12 %. Sand the dry surface and clean it, remove waxes, resins and grease with **NITRO thinner**.

Iron, steel surfaces

Remove rust mechanically, grease and other impurities with **NITRO thinner**.

Galvanised sheet metal, hard PVC

Clean surface with a mixture of water (10 l), ammonium chloride (solution of ammoniac – 0,5 l) and detergent (one cap) and sand with a sanding cloth made of synthetic fibres. Rinse rests of sanding with water thoroughly. The use of a wire brush and metal wool is not allowed!

Cooper, aluminium surface*

Clean surface with **NITRO thinner** and sand with a sanding cloth from synthetic fibres. The use of a wire brush and metal wool is not allowed!

Renovation of old coatings

Clean and sand the undamaged coatings, remove damaged ones completely.



COATING SYSTEMS

| SURFACE | | SURFACE PREPARATION | IMPREGNATION | BASE COAT | FINAL COAT |
|------------------------|--------------------|--|---|--|--|
| WOOD | interior | sanding, Removal of impurities | / | 1x TESSAROL wood primer | 2x TESSAROL professional enamel satin |
| | exterior | | 1x BORI thin-layered stain with biocide | 2x TESSAROL wood primer | |
| IRON, STEEL | Interior | Removal of rust and impurities nečistoč | / | 1x TESSAROL iron primer | |
| | Exterior | | 2x TESSAROL iron primer | | |
| GALVANISED SHEET METAL | Interior | Removal of corrosion products and impurities | / | 1x TESSAROL universal primer | |
| | Exterior | | | 2x TESSAROL universal primer | |
| COPPER, ALUMINIUM* | interior | | | 1x TESSAROL universal basic paint | |
| | exterior | | | 1x TESSAROL universal basic paint | |
| HARD PVC | interior | Removal of impurities | / | 1x TESSAROL universal basic paint | |
| | Exterior | | | | |
| OLD COATS | Interior /exterior | | 1x impregnation or 1 – 2x suitable base coat | 1 - 2x TESSAROL professional enamel Satin | |

REMARKS AND SPECIFICS

- If you remove rust with the chemical agents (based on phosphor acid) you have to rinse surface thoroughly with water, dry and then apply **TESSAROL iron primer**, as the rests of chemical agents prevent drying.
- In the rooms with bad ventilation, strong odour after organic solvents may appear. Therefore we do not recommend alkyd binder based coats for painting of interior furniture parts.
- * prior to painting of aluminium base, beforehand test of adhesion of a coat to the cleaned surface is needed.
- At the application of coatings intermediate coat sanding with fine sanding pads is recommended for intermediate coat adhesion of coatings and better final treatment.